ANTISLIP COLOURED COATING
Premium Concrete Floor Finish

SlipSafe
Anti-Slip coatings, treatments, & compliance specialists

PERFORMANCE FEATURES

- Premium coloured finish for functional and aesthetic use
- VOC-free and environmentally friendly
- Superior durability for medium to high-traffic areas
- UV-resistant for indoor and outdoor use
- Easy to apply and maintain

RECOMMENDED APPLICATIONS

- P3 | INDOOR AND OUTDOOR CONCRETE FLOORS, GARAGES, PARKING AREAS, WALKWAYS
- P4 | STAIRCASES, WAREHOUSES, LIGHT INDUSTRIAL AREAS, RAMPS ≤1:14
- P5 | HIGH-RISK SLIP AREAS, STEEP RAMPS, COMMERCIAL KITCHENS (WHEN COMBINED WITH SLIPSAFE P5 ADDITIVE)

COMPLIANCE & CERTIFICATIONS

- Meets NZS 4586:2004 slip resistance requirements (wet pendulum testing)
- Available slip ratings: P3, P4, P5
- VOC-free, water-based, and non-toxic
- UV-resistant for interior and exterior use

SLIPSAFE NZ – CONSULTATION & SAMPLES

www.slipsafe.co.nz info@slipsafe.co.nz 0508 754 778

ANTISLIP POLISH GRIP
Premium Concrete Floor Finish

SlipSafe
Anti-Slip coatings, treatments, & compliance specialists

INSTALLATION & APPLICATION METHOD

1. Inspect surface and prepare by cleaning thoroughly.
2. For original concrete, apply prime coat diluted 20–25% with water.
3. Apply second coat diluted 0–5% with water.
4. For slip ratings above P3, incorporate SlipSafe Non-Slip Particles into the coating.
5. For P5 rating, add SlipSafe P5 Additive.
6. Allow sufficient drying time between coats.

COMPATIBLE SURFACES

METAL

NATURAL STONE

CONCRETE


TILES

TECHNICAL SPECIFICATIONS

Product Type	Two-pack water-based polyurethane coating
Colour	Light Grey (RAL 7035), Traffic Grey (RAL 7042), Anthracite Grey (RAL 7016), Traffic White (RAL 9016), Traffic Yellow (RAL 1023), custom colours on request
Finish	Coloured Satin
Compatible Surfaces	Concrete, tiles, natural stone, metal (with primer)
Coverage	Varies by surface porosity – refer to pack details
Application	Roller Application
Primer	Required for non-concrete substrates
Slip Rating	P3, P4, P5 (with additive)
Recoat Time	2-3 hours between coats
Longevity	Recoat as required to maintain slip resistance and appearance
Chemical Resistant	
Shelf Life	
Treatment Life	
Storage	Store between 10°C–27°C. Protect from freezing
Expected Service Life	5 years (with correct maintenance)
Maintenance	Clean regularly using a pH-neutral cleaner
Warranty	

SLIPSAFE NZ – CONSULTATION & SAMPLES

www.slipsafe.co.nz info@slipsafe.co.nz 0508 754 778